

ANOTEC Small High Silicon Cast Iron Anodes

PRODUCT DESCRIPTION

Composition: (weight%)

ASTM A 518 Grade 3

Silicon	14.20 – 14.75%	Manganese	1.50% max.
Chromium	3.25 – 5.00%	Copper	0.50% max.
Carbon	0.70 – 1.10%	Molybdenum	0.20% max.

“Chill Cast” in Metal Molds

Anotec's proprietary process assures consistent weight, greater density, less flake graphite grain boundary, and lower chemical segregation than Sand Cast Anodes. The ANOTEC Chill Cast structure is similar to “Spin Cast” tubular Anodes.

Cable Connection Provisions

Anotec manufactures anodes to accommodate customers' connection requirements, including both established industry standard methods and special custom designs whenever warranted by demand.

Special features may be developed to suit requirements on application to the factory.

Performance

Accelerated corrosion tests confirm that Anotec Chill cast Anodes perform significantly better (up to 19%) than sand cast anodes in chloride and sulphate environments. Test reports available on request.



MADE IN NORTH AMERICA

Anotec Small High Silicon Cast Iron Anodes

TYPE	SHAPE	CONNECTION FEATURES	NOMINAL DIMENSIONS		NOMINAL AREA Sq ft (SqM)	NOMINAL WEIGHT lbs. (Kg.)
			inch Diameter	(mm) Length		
2009 (2G9)	Hollow Tube Utility Duct Anode	single or string	2 (51)	9 (230)	.39 (0.36)	4.4 (2.0)
2212 Z 2224 Z 2242 Z 2248 Z	Hollow Tube	Zinc Anchor single or string	2.2 (56)	12 (300)	.6 (.056)	6.2 (2.8)
			2.2 (56)	24 (600)	1.1 (.102)	14.8 (6.7)
			2.2 (56)	42 (1060)	2.0 (.185)	25 (11.4)
			2.2 (56)	48 (1220)	2.3 (.213)	29 (13.1)
2624 Z 2642 Z 2648 Z			2.6 (66)	24 (600)	1.3 (.120)	20 (9.1)
			2.6 (66)	42 (1060)	2.4 (.222)	36 (16.3)
			2.6 (66)	48 (1220)	2.7 (.250)	41 (18.6)
BUTTON 6B3	Hemispherical "Button" with Bolt Hole	Caulked Lead Side or base connection	6 (150)	3 (76)	.33 (.030)	18 (8.2)
BULLET 3B6	Condenser "Bullet" Anode	Threaded Steel Stud	3 (76)	6 (150)	.5 (.046)	12 (5.5)
12B15	Bridge Deck "Pancake" Anode	Caulked Lead	12 (300)	1.5 (38)	1.1 (.102)	40 (18.1)

ANOTEC Industries Ltd.
5701 Production Way, Langley, BC Canada V3A 4N5
Telephone 604.514.1544 Fax 604.514.1546
Web site: www.anotec.com e-mail: info@anotec.com

Distributed by: