

March 05



**ASBURY**  
FOUNDED 1895

A  
S  
B  
U  
R  
Y

## ASBURY NO. 218-F

### PRODUCT DATA SHEET

#### TYPICAL CHEMICAL ANALYSIS (Dry Basis)

Carbon (L.O.I. method)	99.0%
Moisture	0.10%
Ash	0.45%
VCM	0.40%
Sulfur	3.75%

#### TYPICAL PHYSICAL PROPERTIES

Bulk Density (lbs/cu.ft.)	52 - 58
Resistivity @ 150 PSI (Ω-inch)	0.02
(Ω-cm)	0.05

#### TYPICAL SCREEN SIZING

+ 3/8 Mesh	5%
+ 50 Mesh	75%
- 50 Mesh	30%

#### APPLICATION

ASBURY No. 218-F Carbon is a ground grade of the calcined petroleum coke used in our No. 281-L. It is a good choice in situations where the backfill must be slurry pumped into position. The increased bulk density ASBURY No. 218-F provides for excellent anode/carbon contact. No. 218-F should be considered when a non-abrasive, pumpable, backfill is required.

#### PACKAGING

The standard packaging for No. 218-F is a 50 lb. multiwall bag. Pallets are plastic wrapped for weather protection and improved handling characteristics. Grade No. 218-F is also available in supersacks or drums upon request.

C  
A  
R  
B  
O  
N  
S

2  
1  
8  
-  
F

**The Asbury Graphite Mills, Inc.**

Tel: 908-537-2155  
FAX: 908-537-2908

**Asbury Graphite Inc. of California**

Tel: 510-799-3636  
FAX: 510-799-7460

Percentages are not guaranteed, they indicate the approximate physical and chemical analysis. A product should be thoroughly tested and independently concluded satisfactory before application. Customers assume all risk and liability for loss, damage, or injury to their property or the property of others arising from the application of the goods furnished.